

Application No.: 10/761086

Case No.: 58509US002


Amendments to the Claims:

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1. (Currently Amended) Fluoropolymer dispersion comprising fluoropolymer particles having an average particle size of 10 to 400nm dispersed in water, said dispersion having a solids content between 35 and 70% by weight, said dispersion being free of fluorinated surfactant having a molecular weight of less than 1000g/mol or containing said fluorinated surfactant having a molecular weight of less than 1000g/mol in an amount of not more than 0.05% by weight based on the total weight solids of said dispersion, said dispersion further comprising a non-ionic non-fluorinated surfactant or mixture of non-ionic non-fluorinated surfactants and one or more non-fluorinated anionic surfactants, characterized in that the amount and nature of said non-ionic non-fluorinated surfactant or mixture of non-ionic non-fluorinated surfactants is selected such that the Viscosity Transition Temperature (VTT) of said fluoropolymer dispersion is at least 26°C and that the fluoropolymer dispersion is essentially free of aromatic group containing non-ionic surfactants.

2. (Original) Fluoropolymer dispersion according to claim 1 wherein said non-ionic non-fluorinated surfactant or mixture of non-ionic non-fluorinated surfactants can be represented by the general formula:



wherein R^1 represents an aliphatic hydrocarbon group having at least 8 carbon atoms, R^2 represents an alkylene having 3 carbon atoms, R^3 represents hydrogen or a C_1 - C_3 alkyl group, n has a value of 0 to 40, m has a value of 0 to 40 and the sum of $n+m$ being at least 2.

3. (Currently Amended) Fluoropolymer dispersion according to claim 2 wherein m is 0 and wherein said non-ionic non-fluorinated surfactant or mixture of non-ionic non-fluorinated surfactants has a Hydrophilic Lypophilic Balance (HLB) between 11 and 16.

Application No.: 10/761086

Case No.: 58509US002

4. (Original) Fluoropolymer dispersion according to claim 2 wherein said fluoropolymer dispersion comprises a mixture of non-ionic non-fluorinated surfactants comprising one or more non-ionic non-fluorinated surfactants according to formula (I) wherein m is 0 and one or more non-ionic non-fluorinated surfactants according to formula (I) wherein n and m each are different from 0.

5. (Original) Fluoropolymer dispersion according to claim 2 wherein said fluoropolymer dispersion comprises one or more non-ionic non-fluorinated surfactants according to formula (I) and one or more polysorbates.

6. (Original) Fluoropolymer dispersion according to claim 2 wherein said fluoropolymer dispersion comprises one or more non-ionic non-fluorinated surfactants according to formula (I) and one or more ethoxylated acetylenic diols.

7. (Original) Fluoropolymer dispersion according to claim 6 wherein said ethoxylated acetylenic diols have an HLB between 11 and 16.

8. (Original) Fluoropolymer dispersion according to claim 1 wherein the fluoropolymer comprises polytetrafluoroethylene.

9. (Currently Amended) A method comprising, coating or impregnating a substrate with the Use of fluoropolymer dispersion as defined in claim 1 ~~in coating or impregnation of a substrate.~~

10. (Currently Amended) A method Use according to claim 9 wherein said substrate comprises metal substrates, glass fiber fabrics, polymeric substrates and paper.

Application No.: 10/761086

Case No.: 58509US002

11. (Currently Amended) Method of providing a fluoropolymer particle dispersion comprising:

- (a) providing a fluoropolymer dispersion comprising fluoropolymer particles having an average particle size of 10 to 400nm and comprising fluorinated surfactant having a molecular weight of less than 1000g/mol or being free thereof;
- (b) reducing the amount of said fluorinated surfactant in said dispersion if the amount thereof is more than 0.05% by weight based on the total weight of solids of the dispersion in the presence of a non-ionic non-fluorinated surfactant or mixture of non-ionic non-fluorinated surfactants;
- (c) upconcentrating the fluoropolymer dispersion in the presence of a non-ionic non-fluorinated surfactant or mixture of non-ionic non-fluorinated surfactants so as to increase the amount of fluoropolymer solids in said dispersion to a level between 35% and 75% by weight; and
- (d) adding one or more non-fluorinated anionic surfactants to the fluoropolymer dispersion prior to or after upconcentrating said fluoropolymer dispersion;

wherein said non-ionic non-fluorinated surfactant or mixture of non-ionic non-fluorinated surfactants used in said step (b) and/or (c) are selected such that the fluoropolymer dispersion after step (d) has a Viscosity Transition Temperature (VTT) of at least 26°C or alternatively, further one or more non-ionic non-fluorinated surfactants are added to adjust the Viscosity Transition Temperature (VTT) of the fluoropolymer dispersion to at least 26°C and wherein said non-ionic non-fluorinated surfactants are selected such that the fluoropolymer dispersion is free from aromatic group containing non-ionic surfactant.